

Bio-Inspired Self-Healing Nanostructures for Environmental Pollutant Degradation and Biomedical Diagnostics

Albina^{1*}, Sawera Malik², Neelam Zeb³, Hafsa Urooj⁴, Kiran Fatima⁵, Atiq Parveen⁶, Rabiya Bashir⁷

¹Department of Biotechnology and Genetic Engineering, University of Agriculture Peshawar, Pakistan

²Department of Chemistry, Government College University of Faisalabad, Pakistan

³Department of Biotechnology, Women University Mardan, Pakistan

⁴Department of Biotechnology and Genetic Engineering, University of Agriculture Peshawar, Pakistan

⁵Department of Chemistry, University of Sialkot, Pakistan

⁶Department of Chemistry, Government College University of Faisalabad, Pakistan

⁷Department of Botany, University of Agriculture Faisalabad, Pakistan

DOI: <https://doi.org/10.36347/sjmcr.2026.v14i10.005>

| Received: 11.07.2026 | Accepted: 06.09.2026 | Published: 05.10.2026

*Corresponding author: Albina

Department of Biotechnology and Genetic Engineering, University of Agriculture Peshawar, Pakistan

Abstract

Review Article

Bio-inspired self-healing nanostructures mimic biological repair processes skin regeneration, bone remodeling, plant vascular reconnection using dynamic covalent chemistry, supramolecular assembly, hydrogen bonding, and metal-ligand coordination to recover mechanical strength, conductivity, and catalytic activity after damage. In environmental remediation, they resist the catalyst deactivation and fatigue limiting conventional photocatalysts, adsorbents, and membranes, sustaining degradation of dyes, pharmaceuticals, pesticides, and heavy metals over far more cycles. In biomedical diagnostics, the same repair logic enables biosensors, wearables, implants, and wound dressings that tolerate repeated mechanical deformation without losing sensitivity. AI and computational modeling are now accelerating design by predicting healing efficiency before synthesis, though scalable fabrication, long-term stability, nanotoxicity, and regulatory approval remain unresolved. This review covers the biological inspiration, material classes, healing mechanisms, applications, and key challenges facing this field.

Keywords: Bio-inspired nanomaterials; self-healing nanostructures; environmental remediation; biomedical diagnostics; nanotechnology; biosensors; artificial intelligence; photocatalysis; tissue engineering.

Copyright © 2026 The Author(s): This is an open-access article distributed under the terms of the Creative Commons Attribution 4.0 International License (CC BY-NC 4.0) which permits unrestricted use, distribution, and reproduction in any medium for non-commercial use provided the original author and source are credited.

1. INTRODUCTION

The twenty-first century has witnessed unprecedented progress in nanotechnology, materials science, and biomedical research, leading to multifunctional materials with applications ranging from environmental remediation to precision medicine. Despite these advances, conventional materials face significant limitations associated with structural degradation, mechanical fatigue, catalyst deactivation, surface fouling, and irreversible damage during prolonged operation. Such deterioration reduces performance, shortens operational lifetime, increases maintenance costs, and limits sustainability. Consequently, the development of intelligent materials capable of autonomously restoring structure and functionality has become a major research priority (Wang & Urban, 2020; White *et al.*, 2001).

Nature provides numerous examples of efficient self-repair systems. Human skin rapidly repairs wounds through coordinated cellular regeneration, bones continuously remodel damaged tissues, vascular systems seal injuries through clotting mechanisms, and plants regenerate damaged organs following injury (Song *et al.*, 2024; Zhao *et al.*, 2021). These biological systems demonstrate remarkable adaptability through intrinsic mechanisms capable of detecting damage, activating repair pathways, and restoring integrity with minimal external intervention. The exceptional efficiency of these natural regenerative processes has inspired scientists to develop synthetic materials that mimic similar healing behavior at the molecular and nanoscale levels (Holtzen-Andersen *et al.*, 2011; Zhao *et al.*, 2021).

Bio-inspired self-healing nanostructures represent an emerging class of advanced materials designed to imitate biological repair mechanisms while

incorporating the unique physicochemical properties of nanomaterials. Unlike conventional materials that accumulate irreversible damage, self-healing nanostructures utilize reversible molecular interactions, dynamic covalent bonds, supramolecular assemblies, hydrogen bonding, metal-ligand coordination, and stimuli-responsive networks to repair structural defects and recover functional performance (Chen *et al.*, 2002; Holten-Andersen *et al.*, 2011; Sun *et al.*, 2018; Wu *et al.*, 2023). These adaptive mechanisms enable repeated restoration of mechanical strength, electrical conductivity, catalytic activity, and surface functionality, significantly extending material lifespan (Wang & Urban, 2020; Yang & Urban, 2013).

The incorporation of nanotechnology has expanded the capabilities of self-healing materials by introducing high surface-area-to-volume ratios, tunable electronic properties, enhanced catalytic efficiency, and superior mechanical performance. Nanomaterials including graphene and derivatives, carbon nanotubes (CNTs), metal nanoparticles, metal-organic frameworks (MOFs), covalent organic frameworks (COFs), MXenes, polymeric nanoparticles, conductive hydrogels, nanozymes, and hybrid nanocomposites have been successfully integrated into self-healing systems to produce multifunctional materials with enhanced durability and responsiveness (Kausar, 2021; C. Wang *et al.*, 2019; Self *et al.*, 2023; Xie *et al.*, 2024; Zhang *et al.*, 2020).

Environmental remediation has significantly benefited from these developments. Increasing industrialization, agricultural intensification, and population growth have led to continuous release of hazardous contaminants into ecosystems. Persistent pollutants such as synthetic dyes, pharmaceutical residues, pesticides, heavy metals, microplastics, and PFAS pose serious threats to biodiversity and human health. Conventional treatment technologies often suffer from catalyst deactivation, membrane fouling, and declining efficiency during long-term operation. Bio-inspired self-healing nanostructures offer an attractive alternative by autonomously restoring catalytic activity, regenerating adsorption sites, and repairing structural damage (C. Yang *et al.*, 2023; Louis *et al.*, 2021; Tripathy & Pradhan, 2025; Xie *et al.*, 2024).

In biomedical diagnostics, self-healing nanostructures have gained attention owing to increasing demand for flexible, durable, and highly sensitive healthcare technologies. Modern diagnostic systems including wearable biosensors, implantable devices, and tissue-engineering scaffolds are routinely exposed to mechanical deformation and physiological stress that gradually degrade performance. The incorporation of self-healing mechanisms enables autonomous restoration of electrical conductivity, sensing capability, and mechanical integrity, significantly enhancing

reliability for long-term health monitoring (Chae *et al.*, 2023; Huang *et al.*, 2024; Xu & Hsu, 2023).

The rapid evolution of computational materials science has further accelerated progress in this field. Artificial intelligence, machine learning, molecular dynamics simulations, density functional theory (DFT), and high-throughput computational screening have transformed the discovery and optimization of advanced nanomaterials. These computational tools facilitate rapid prediction of healing efficiency, mechanical performance, and biocompatibility, substantially reducing experimental time and cost (C. Chen *et al.*, 2020; Ludwig *et al.*, 2023). Integration of AI with advanced manufacturing technologies such as 3D printing, electrospinning, and microfluidics has created new opportunities for designing complex multifunctional nanostructures with precisely controlled architectures.

Despite remarkable progress, challenges related to scalable fabrication, long-term stability, environmental safety, nanotoxicity, regulatory approval, and commercial translation continue to limit practical implementation. This review provides a comprehensive assessment of recent advances in bio-inspired self-healing nanostructures with emphasis on design principles, biological inspiration, healing mechanisms, material classifications, fabrication techniques, characterization methods, environmental applications, biomedical diagnostics, AI-assisted optimization, challenges, and future opportunities.

2. Fundamentals of Bio-Inspired Self-Healing Nanostructures

Bio-inspired self-healing nanostructures are intelligent materials designed to imitate autonomous repair mechanisms found in biological organisms. Unlike conventional nanomaterials that undergo irreversible degradation after repeated damage, these advanced materials possess the intrinsic or extrinsic ability to restore structural integrity and functional performance through dynamic molecular interactions (X. Li *et al.*, 2024; Wang & Urban, 2020). Their development represents the convergence of nanotechnology, materials science, chemistry, biology, and biomedical engineering.

Self-healing nanostructures operate through reversible molecular interactions such as hydrogen bonding, dynamic covalent chemistry, metal-ligand coordination, supramolecular assembly, ionic interactions, and host-guest recognition (Holten-Andersen *et al.*, 2011; Sun *et al.*, 2018; Wu *et al.*, 2023; Zhang *et al.*, 2022). When structural damage occurs, these reversible interactions reorganize the molecular network, reconnect fractured interfaces, and recover original properties. Depending on material design, healing may occur spontaneously under ambient conditions or be activated by external stimuli such as

heat, light, moisture, pH, magnetic fields, or electrical fields.

Based on healing strategy, self-healing systems are categorized into intrinsic and extrinsic materials. Intrinsic self-healing systems rely on reversible chemical interactions incorporated directly within the polymer or nanocomposite network. Because these interactions can repeatedly dissociate and reform, intrinsic systems exhibit multiple healing cycles without requiring

additional healing agents (Ahn *et al.*, 2014; Wang & Urban, 2020). Extrinsic self-healing systems contain encapsulated healing agents stored within microcapsules, hollow fibers, or vascular networks that rupture upon damage and release repair materials (White *et al.*, 2001; Zamal *et al.*, 2020). Although extrinsic systems often exhibit excellent healing efficiency, their capacity is limited by finite healing agent quantities (Zamal *et al.*, 2020).




Figure 1: Schematic of (a) intrinsic self-healing via dynamic covalent networks and (b) extrinsic self-healing via microcapsule-based systems

The incorporation of nanomaterials has substantially improved material performance. Nanostructures such as graphene, graphene oxide, carbon nanotubes, metal nanoparticles, MXenes, quantum dots, MOFs, COFs, cellulose nanofibers, and nanozymes provide exceptional mechanical strength, electrical conductivity, catalytic activity, and surface functionality (Kausar, 2021; Self *et al.*, 2023; Xie *et al.*, 2024; Zhang *et al.*, 2020). These nanoscale building blocks reinforce polymer matrices and participate actively in dynamic healing processes by facilitating intermolecular interactions and improving structural organization.

Modern self-healing materials are frequently designed to combine autonomous healing with electrical

conductivity, antibacterial activity, photocatalytic degradation, pollutant adsorption, drug delivery, biosensing, and tissue regeneration (Dalei *et al.*, 2024; Liu & Hsu, 2023; Xiao *et al.*, 2022; Y. Yang *et al.*, 2024). Such multifunctionality is particularly valuable in environmental remediation and biomedical diagnostics, where materials must maintain continuous performance under mechanically demanding and chemically complex conditions.

Healing efficiency is commonly evaluated as the percentage recovery of a material property after damage. Mechanical healing efficiency is determined by comparing tensile strength or fracture toughness before and after healing, while electrical healing efficiency is evaluated through recovery of conductivity (Wang &

Urban, 2020; Yang & Urban, 2013). High-performance intrinsic self-healing nanostructures frequently achieve healing efficiencies exceeding 90%, demonstrating their potential for practical applications (X. Li *et al.*, 2024; Wang & Urban, 2020).

Recent advances in dynamic polymer chemistry have enabled increasingly sophisticated self-healing systems. Dynamic covalent networks based on Schiff-base reactions, disulfide exchange, boronic ester formation, Diels–Alder reactions, and acylhydrazone chemistry provide strong yet reversible chemical linkages (Chen *et al.*, 2002; Dalei *et al.*, 2024; Sun *et al.*, 2018; Zhang *et al.*, 2022). Supramolecular materials employing hydrogen bonding, π – π interactions, and metal–ligand coordination exhibit rapid self-repair while maintaining flexibility and adaptability (Holten-Andersen *et al.*, 2011; Wu *et al.*, 2023). The combination of multiple dynamic interactions has further enhanced healing efficiency and mechanical performance.

3. Biological Inspiration

The extraordinary regenerative capabilities of living organisms have long served as inspiration for

developing advanced materials with autonomous repair functions (Zhao *et al.*, 2021). Biological systems possess sophisticated mechanisms enabling detection of damage, coordination of repair processes, and restoration of structural integrity while maintaining normal physiological function.

Nature demonstrates remarkable examples of autonomous repair across multiple levels of biological organization. Human skin rapidly repairs injuries through coordinated hemostasis, inflammation, cell proliferation, and tissue remodeling. Bone continuously undergoes remodeling through balanced activities of osteoclasts and osteoblasts, allowing damaged tissue replacement while preserving mechanical strength. Plants regenerate injured tissues through cell dedifferentiation, callus formation, and vascular reconnection. Marine mussels maintain strong adhesion under harsh aquatic conditions through catechol-rich adhesive proteins, while spider silk combines exceptional strength and elasticity through hierarchical molecular organization (Han *et al.*, 2018; Waite *et al.*, 2005; Yu *et al.*, 2013).




Figure 2: Biological self-healing systems (skin, bone, mussels, plants) and their nanomaterial mimics (hydrogels, polymers, metal-ligand networks, microchannels)

Human skin's wound-healing process involves highly coordinated biochemical signaling pathways. Immediately after injury, blood coagulation prevents

excessive bleeding, followed by immune cell recruitment to eliminate pathogens. Fibroblasts subsequently synthesize extracellular matrix components including

collagen to restore tissue architecture, while epithelial cells migrate to close the wound surface. This dynamic repair process has inspired self-healing hydrogels, wound dressings, and tissue-engineering scaffolds capable of mimicking natural skin regeneration (Song *et al.*, 2024; Talebian *et al.*, 2019; Y. Yang *et al.*, 2024).

Bone remodeling has inspired mechanically robust self-healing materials. Unlike inert structural materials, bone continuously senses mechanical stress and repairs microscopic damage before catastrophic failure occurs. This adaptive remodeling process has motivated polymer nanocomposites and hybrid materials combining high mechanical strength with repeated healing capability (X. Li *et al.*, 2024; Yang & Urban, 2013).

Plant regeneration provides another valuable source of inspiration. Following mechanical injury or pathogen attack, plants activate complex signaling networks stimulating cell proliferation, tissue differentiation, and vascular reconstruction. The remarkable regenerative capacity of plant tissues has encouraged utilization of renewable biopolymers such as cellulose, lignin, and pectin for constructing environmentally sustainable self-healing materials.

At the molecular level, biological systems rely predominantly on reversible interactions rather than permanent chemical bonds. Hydrogen bonding, electrostatic interactions, hydrophobic associations, metal-ion coordination, and reversible enzymatic reactions collectively provide flexibility necessary for repeated repair (Holten-Andersen *et al.*, 2011; Yu *et al.*, 2013). Modern self-healing nanostructures reproduce these dynamic interactions using synthetic polymers, supramolecular chemistry, and functional nanomaterials (Ahn *et al.*, 2014; Han *et al.*, 2018; Waite *et al.*, 2005).

Biological repair systems exhibit hierarchical organization extending from molecular and nanoscale components to macroscopic structures, allowing efficient distribution of mechanical stress and localized repair. This principle has been widely adopted in nanomaterial engineering, where hierarchical assemblies of nanoparticles, nanofibers, nanosheets, and polymer matrices provide improved mechanical performance while facilitating efficient healing (X. Li *et al.*, 2024; Zhao *et al.*, 2021).

4. Classification of Bio-Inspired Self-Healing Nanostructures

4.1 Classification Based on Healing Strategy

Intrinsic Self-Healing Nanostructures:

These materials possess reversible chemical interactions integrated directly into their molecular framework, allowing repeated repair without external healing agents. Common reversible interactions include hydrogen bonding, dynamic covalent chemistry, ionic interactions, host-guest recognition, supramolecular

assembly, and metal-ligand coordination (Ahn *et al.*, 2014; Holten-Andersen *et al.*, 2011; Sun *et al.*, 2018; Wu *et al.*, 2023). Intrinsic systems exhibit excellent repeatability and long operational lifetimes, making them preferred for wearable electronics, flexible biosensors, artificial skin, conductive hydrogels, and implantable devices (Chae *et al.*, 2023; Huang *et al.*, 2024; L. Li *et al.*, 2023).

Extrinsic Self-Healing Nanostructures:

These systems employ encapsulated healing agents stored within microcapsules, hollow fibers, or vascular-like microchannels. Mechanical damage ruptures reservoirs, releasing healing agents that polymerize and repair damaged regions (White *et al.*, 2001; Zamal *et al.*, 2020). Although extrinsic systems achieve rapid healing and high initial recovery, performance gradually declines as healing agents become depleted. They are more suitable for applications where damage occurs infrequently, such as protective coatings and structural composites (Zamal *et al.*, 2020).

4.2 Classification Based on Material Composition

Polymeric Nanocomposites:

These constitute one of the largest classes of self-healing materials, consisting of polymer matrices reinforced with nanoscale fillers. Common polymer matrices include polyurethane, polyvinyl alcohol, polyethylene glycol, and epoxy resins. Nanofillers such as graphene oxide, silica nanoparticles, cellulose nanofibers, and carbon nanotubes improve structural stability and facilitate dynamic molecular interactions (Kausar, 2021; C. Wang *et al.*, 2019; Self *et al.*, 2023; Zamal *et al.*, 2020).

Self-Healing Hydrogels:

These three-dimensional polymeric networks absorb large quantities of water while maintaining structural integrity. Their high water content resembles natural soft tissues, making them suitable for biomedical applications. Self-healing hydrogels rely on hydrogen bonding, Schiff-base reactions, boronic ester chemistry, metal-ion coordination, or supramolecular interactions to restore damaged networks (Dalei *et al.*, 2024; Sun *et al.*, 2018; Wu *et al.*, 2023; Zhang *et al.*, 2022).

Carbon-Based Nanostructures:

Graphene, graphene oxide, carbon nanotubes, and carbon quantum dots possess exceptional electrical, mechanical, and thermal properties. They improve electrical conductivity, mechanical reinforcement, and photocatalytic activity, making them valuable for flexible electronics, environmental sensors, photocatalysts, and biomedical platforms (Kausar, 2021; Louis *et al.*, 2021; Self *et al.*, 2023; C. Wang *et al.*, 2019).

Metal-Organic Frameworks (MOFs):

These crystalline porous materials composed of metal ions connected through organic ligands offer

exceptionally high surface area, tunable pore structure, and adjustable surface chemistry. Integration of dynamic coordination chemistry has enabled self-healing frameworks capable of maintaining structural integrity under repeated operational conditions (C. Yang *et al.*, 2023; Xie *et al.*, 2024; Yuan *et al.*, 2024).

MXene-Based Nanostructures:

These two-dimensional transition metal carbides, nitrides, and carbonitrides exhibit excellent electrical conductivity, hydrophilicity, and mechanical flexibility. Surface functional groups facilitate strong intermolecular interactions with polymer matrices, enabling efficient self-healing conductive composites for wearable sensors, supercapacitors, and flexible electronics (Cai *et al.*, 2020; Chae *et al.*, 2023; L. Li *et al.*, 2023; Zhang *et al.*, 2020).

Nanozymes:

These nanomaterials mimic catalytic activity of natural enzymes while exhibiting superior stability and lower production costs. Integration into self-healing matrices has enabled intelligent catalytic systems for pollutant degradation, biosensing, and antimicrobial applications (Xiao *et al.*, 2022).

4.3 Classification Based on Stimuli Responsiveness

Many self-healing nanostructures require external stimuli to initiate or accelerate healing. Thermally responsive materials activate reversible chemical reactions upon heating. Photoresponsive materials utilize ultraviolet or visible light to trigger molecular rearrangements. pH-responsive systems exploit changes in acidity or alkalinity to regulate bond formation. Electrically responsive materials utilize electrical stimulation for localized healing (Huang *et al.*, 2024; Song *et al.*, 2024). Multi-stimuli-responsive systems combine multiple activation mechanisms, allowing adaptive responses under complex conditions

5. Self-Healing Mechanisms

Dynamic Covalent Chemistry:

This approach utilizes reversible covalent bonds that can dissociate and reform under appropriate conditions. Dynamic reactions incorporated into self-healing nanostructures include Schiff-base reactions, boronic ester formation, disulfide exchange, Diels–Alder cycloaddition, and acylhydrazone chemistry (Chen *et al.*, 2002; Dalei *et al.*, 2024; Sun *et al.*, 2018; Zhang *et al.*, 2022). These reversible reactions combine strong mechanical stability with repeated healing capability.

Hydrogen Bonding:

This represents one of the simplest yet most versatile self-healing mechanisms. Although individual hydrogen bonds are relatively weak, their collective strength enables rapid molecular rearrangement while preserving overall material integrity. Hydrogen-bonded polymer networks exhibit fast healing under ambient conditions, excellent flexibility, and high elasticity (Sun *et al.*, 2018; Wu *et al.*, 2023).

Supramolecular Interactions:

These rely on reversible non-covalent interactions including host–guest recognition, π – π stacking, hydrophobic interactions, electrostatic attraction, and van der Waals forces. Because supramolecular interactions operate under mild conditions, they are widely employed in injectable hydrogels, tissue-engineering scaffolds, and drug delivery systems (S. Li *et al.*, 2023; Nejati & Mongeau, 2023; Talebian *et al.*, 2019).

Metal–Ligand Coordination:

Coordination bonds formed between metal ions and organic ligands combine mechanical strength with dynamic reversibility. Transition metal ions such as Fe^{3+} , Zn^{2+} , Ca^{2+} , and Cu^{2+} readily coordinate with functional ligands to form adaptive polymer networks (Holtén-Andersen *et al.*, 2011; Yu *et al.*, 2013). Mussel-inspired catechol chemistry represents a successful example for self-healing adhesives and conductive hydrogels (Han *et al.*, 2018; Waite *et al.*, 2005).

Self-Assembly:

This enables molecules, polymers, or nanoparticles to spontaneously organize into highly ordered structures through thermodynamically favorable interactions. During damage, disrupted assemblies can reorganize and restore original nanostructure without external intervention (Ahn *et al.*, 2014; X. Li *et al.*, 2024).

Stimuli-Responsive Healing:

Many advanced systems combine autonomous repair with external stimuli to accelerate or enhance healing efficiency. Heat promotes molecular mobility and dynamic bond exchange. Light activates photoresponsive molecular switches or initiates photopolymerization. Electrical and magnetic fields enable localized heating or molecular alignment (Huang *et al.*, 2024; Song *et al.*, 2024). Moisture and pH changes regulate reversible chemical interactions within hydrogel networks.




Figure 3: Comparative performance of self-healing mechanisms showing (a) healing efficiency and (b) healing speed

6. Synthesis and Fabrication Techniques

Sol-Gel Method:

This widely employed technique synthesizes inorganic and hybrid nanomaterials through hydrolysis and condensation reactions, generating highly uniform porous networks suitable for photocatalysis, sensing, and membrane fabrication (Louis *et al.*, 2021; Xie *et al.*, 2024).

Hydrothermal and Solvothermal Synthesis:

These methods enable controlled crystal growth under elevated temperature and pressure, producing nanostructures with excellent crystallinity and tunable morphology.

Self-Assembly:

This bottom-up approach exploits spontaneous molecular organization through non-covalent interactions, forming highly ordered nanostructures while minimizing energy consumption. Self-assembled materials frequently exhibit improved healing efficiency owing to dynamic molecular organization (Ahn *et al.*, 2014; X. Li *et al.*, 2024).

Electrospinning:

This technique produces ultrafine nanofibers with exceptionally high surface-area-to-volume ratios. Electrospun nanofibrous membranes closely resemble the extracellular matrix, making them valuable for wound healing, tissue engineering, filtration membranes,

and controlled drug delivery (S. Li *et al.*, 2023; Nejati & Mongeau, 2023; Talebian *et al.*, 2019).

Three-Dimensional (3D) Printing:

Advances in 3D printing have revolutionized fabrication by enabling precise control over complex architectures and internal microstructures. Incorporation of dynamic polymer networks into printable inks has facilitated customized biomedical implants, flexible electronics, soft robotics, and intelligent wearable devices (Song *et al.*, 2024; Xu & Hsu, 2023).

Microfluidic Technologies:

These provide precise control over nanoparticle synthesis, capsule formation, and vascular-inspired healing systems by manipulating fluids within microscale channels, improving material uniformity, reproducibility, and scalability (Zamal *et al.*, 2020).

Green Synthesis:

This environmentally sustainable approach utilizes plant extracts, microorganisms, natural polymers, and biodegradable crosslinking agents to replace toxic reducing agents and organic solvents, reducing environmental impacts while improving biocompatibility (Dalei *et al.*, 2024).

7. Characterization Techniques

Morphological Characterization:

Scanning Electron Microscopy (SEM) evaluates surface morphology, crack formation, crack

closure, and structural recovery. Transmission Electron Microscopy (TEM) provides higher spatial resolution for visualizing individual nanoparticles, lattice structures, and interfacial interactions. Atomic Force Microscopy (AFM) measures nanoscale surface topography and mechanical properties simultaneously.

Structural Characterization:

X-ray Diffraction (XRD) identifies crystalline phases, determines crystal structure, and monitors structural changes following healing cycles. Small-Angle X-ray Scattering (SAXS) provides information regarding nanoscale structural organization and hierarchical assembly.

Chemical Characterization:

Fourier Transform Infrared Spectroscopy (FTIR) detects functional groups participating in reversible interactions. Raman Spectroscopy is particularly useful for carbon-based nanomaterials (Kausar, 2021; Self *et al.*, 2023). X-ray Photoelectron Spectroscopy (XPS) determines elemental composition and chemical bonding. Nuclear Magnetic Resonance (NMR) provides molecular-level information regarding reversible covalent reactions (Sun *et al.*, 2018; Zhang *et al.*, 2022).

Thermal Characterization:

Thermogravimetric Analysis (TGA) measures thermal degradation and compositional stability. Differential Scanning Calorimetry (DSC) determines glass transition temperature, melting temperature, and crystallization behavior.

Mechanical Characterization:

Common tests include tensile strength, compression, flexural testing, fracture toughness analysis, dynamic mechanical analysis (DMA), and nanoindentation. Healing efficiency is calculated by comparing recovered mechanical property after healing with original value (Wang & Urban, 2020; Yang & Urban, 2013).

Electrochemical Characterization:

Electrochemical Impedance Spectroscopy (EIS) evaluates charge-transfer resistance and conductivity. Cyclic Voltammetry (CV) measures electrochemical activity, while Galvanostatic Charge-Discharge (GCD) testing is used for energy-storage materials (Cai *et al.*, 2020; Chae *et al.*, 2023; Zhang *et al.*, 2020).

Biological Characterization:

Assessments include cell viability assays, live/dead staining, hemocompatibility testing, antibacterial activity, cell adhesion, proliferation, inflammatory response, and in vivo biocompatibility studies (Xiao *et al.*, 2022; Y. Yang *et al.*, 2024).

In Situ Characterization:

Recent advances enable direct observation of healing mechanisms under realistic conditions through in situ SEM, TEM, Raman spectroscopy, optical microscopy, and synchrotron X-ray imaging.

8. Environmental Applications

Photocatalytic Degradation:

Traditional photocatalysts gradually lose efficiency because of nanoparticle aggregation, surface poisoning, and photocorrosion. Self-healing photocatalytic nanostructures overcome these limitations by continuously restoring damaged catalytic sites. Graphene-based composites, TiO₂ nanostructures, ZnO nanoparticles, MOFs, and MXene-supported photocatalysts have demonstrated enhanced degradation efficiencies for dyes including methylene blue, rhodamine B, and methyl orange (Louis *et al.*, 2021; Xie *et al.*, 2024).

Heavy Metal Removal:

Self-healing nanostructures improve removal of lead, cadmium, mercury, arsenic, and chromium through adsorption, ion exchange, surface complexation, and photocatalytic reduction. Dynamic polymer networks regenerate adsorption sites after saturation, enabling repeated cycles without substantial efficiency loss. Hydrogels incorporating graphene oxide, cellulose nanofibers, chitosan, and MOFs have shown remarkable adsorption capacities (Xie *et al.*, 2024; C. Yang *et al.*, 2023; Yuan *et al.*, 2024).

Pharmaceutical Pollutant Degradation:

Self-healing photocatalysts and nanozyme-based systems have demonstrated efficient degradation of antibiotics, analgesics, and hormones through advanced oxidation processes involving hydroxyl and superoxide radicals (Xiao *et al.*, 2022).

Pesticide Removal:

Self-healing nanostructures incorporating photocatalysts, nanozymes, and porous adsorbents effectively degrade organophosphate pesticides, carbamates, herbicides, and insecticides through catalytic oxidation and adsorption (Louis *et al.*, 2021; Xiao *et al.*, 2022).

Oil–Water Separation:

Self-healing membranes with superhydrophobic and superoleophilic surfaces exhibit excellent oil-water separation performance. Inspired by the lotus leaf effect, these materials maintain surface functionality despite mechanical abrasion through autonomous regeneration of hierarchical architecture (Tu *et al.*, 2025).

Air Purification:

Self-healing photocatalytic coatings based on TiO₂, graphene composites, and MOFs continuously regenerate active catalytic surfaces, enabling long-term

degradation of volatile organic compounds, nitrogen oxides, and sulfur dioxide (Louis *et al.*, 2021; Xie *et al.*, 2024).

Self-Healing Filtration Membranes:

These membranes incorporate reversible molecular networks capable of repairing microcracks and restoring permeability after physical damage,

significantly improving durability and pollutant removal efficiency (Tripathy & Pradhan, 2025).

Environmental Sensors:

Self-healing conductive nanocomposites containing graphene, carbon nanotubes, MXenes, and conductive polymers enable flexible sensors capable of detecting heavy metals, toxic gases, pesticides, and organic pollutants with reliable long-term operation (Cai *et al.*, 2020; Chae *et al.*, 2023; Zhang *et al.*, 2020).




Figure 4: Self-healing nanostructures for environmental remediation (photocatalysis, adsorption, oil-water separation) and biomedical diagnostics (biosensors, wound dressings, implants)

9. Biomedical Applications

Self-Healing Biosensors:

Traditional biosensors suffer from crack formation, electrode degradation, and signal instability after mechanical deformation. Incorporation of dynamic polymer networks reinforced with conductive nanomaterials enables autonomous restoration of damaged sensing pathways. Self-healing biosensors have been developed for detecting glucose, lactate, cholesterol, uric acid, cortisol, dopamine, and cancer-associated proteins (Cai *et al.*, 2020; Chae *et al.*, 2023; L. Li *et al.*, 2023).

Wearable Healthcare Devices:

Self-healing nanostructures have enabled flexible conductive hydrogels and polymer nanocomposites capable of repeatedly restoring

electrical conductivity following mechanical damage. Devices have been successfully developed for monitoring electrocardiogram, electromyography, electroencephalography, blood glucose, sweat composition, body temperature, pulse rate, and human motion (L. Li *et al.*, 2023; C. Wang *et al.*, 2019; Zhang *et al.*, 2020).

Electronic Skin (E-Skin):

Designed to mimic sensory capabilities and mechanical flexibility of human skin, electronic skin integrates self-healing polymers with conductive nanomaterials for detecting pressure, strain, temperature, humidity, and tactile stimuli. Self-healing electronic skin demonstrates rapid recovery of electrical conductivity after repeated cutting, stretching, and compression (Cai *et al.*, 2020; Huang *et al.*, 2024; Song *et al.*, 2024).

Smart Wound Dressings:

Self-healing hydrogels combine excellent water retention, biocompatibility, antibacterial activity, and autonomous repair capability. Incorporation of silver nanoparticles, zinc oxide nanoparticles, graphene oxide, and nanozymes enhances antibacterial activity, antioxidant capacity, angiogenesis, and tissue regeneration. Advanced dressings integrate biosensing capabilities for monitoring wound pH, temperature, oxygen concentration, and infection (Xiao *et al.*, 2022; Y. Yang *et al.*, 2024).

Tissue Engineering and Regenerative Medicine:

Self-healing hydrogels and nanocomposite scaffolds provide injectability, structural adaptability, mechanical resilience, and repeated healing capability. Applications include regeneration of skin, cartilage, bone, cardiac tissue, neural tissue, blood vessels, and skeletal muscle (S. Li *et al.*, 2023; Liu & Hsu, 2023; Nejati & Mongeau, 2023; Talebian *et al.*, 2019).

Implantable Biomedical Devices:

Self-healing nanostructures improve implant reliability by autonomously restoring electrical pathways and mechanical integrity after deformation. Flexible conductive hydrogels reinforced with graphene, MXenes, and conductive polymers have enabled implantable strain sensors, neural interfaces, and cardiac

electrodes with extended operational lifetimes (Xu & Hsu, 2023; Zhang *et al.*, 2020).

Targeted Drug Delivery Systems:

Self-healing hydrogels and nanoparticle-based carriers encapsulate therapeutic agents and release them in response to specific physiological stimuli. Following structural disruption, reversible polymer networks autonomously restore carrier integrity, enabling sustained drug release for anticancer drugs, antibiotics, anti-inflammatory agents, growth factors, and nucleic acids (Dalei *et al.*, 2024).

Bioimaging and Disease Diagnosis:

Fluorescent carbon dots, quantum dots, magnetic nanoparticles, and nanozymes incorporated into self-healing polymer networks support fluorescence imaging, magnetic resonance imaging, computed tomography, and photoacoustic imaging for early diagnosis of cancer, cardiovascular diseases, and neurological disorders (Xiao *et al.*, 2022).

10. Artificial Intelligence and Machine Learning in Design and Optimization

AI, ML, and computational materials science have emerged as powerful tools for accelerating discovery, optimization, and practical implementation of bio-inspired self-healing nanostructures (C. Chen *et al.*, 2020; Ludwig *et al.*, 2023).




Figure 5: AI-driven design and optimization pipeline integrating data collection, feature extraction, ML model training, prediction, and experimental validation with iterative feedback loops

AI-Assisted Materials Discovery:

Machine learning models analyze experimental databases to predict healing efficiency, tensile strength, electrical conductivity, catalytic activity, and biocompatibility before material synthesis (C. Chen *et al.*, 2020; Ludwig *et al.*, 2023).

Computational Modeling:

Density Functional Theory (DFT) investigates electronic structure, charge transfer, and catalytic activity. Molecular Dynamics (MD) simulations provide insight into polymer chain mobility, nanoparticle interactions, crack propagation, and healing kinetics (C. Chen *et al.*, 2020).

AI in Environmental Applications:

Machine learning models optimize photocatalyst composition, predict adsorption capacity, design multifunctional membranes, monitor water quality, predict catalyst lifetime, and optimize wastewater treatment processes (Louis *et al.*, 2021; Xie *et al.*, 2024).

AI in Biomedical Diagnostics:

Deep learning algorithms improve biosensor performance by enhancing signal processing, noise reduction, and biomarker recognition. Applications include continuous glucose monitoring, cardiovascular disease detection, cancer biomarker analysis, and smart wearable diagnostics (Ludwig *et al.*, 2023).

Future Perspectives:

Development will increasingly rely on AI-guided materials discovery, autonomous laboratories, digital twins, robotics, and high-throughput experimentation (C. Chen *et al.*, 2020; Ludwig *et al.*, 2023).

11. Challenges and Future Perspectives**Scalability and Manufacturing:**

Translating laboratory-scale synthesis to industrial production presents difficulties including complex protocols, expensive precursors, stringent reaction conditions, and limited batch-to-batch reproducibility (Kausar, 2021; Zamal *et al.*, 2020).

Long-Term Stability and Durability:

The degradation of dynamic molecular networks under oxidative stress, hydrolytic conditions, ultraviolet radiation, mechanical fatigue, and biological environments requires thorough investigation (Wang & Urban, 2020; Yang & Urban, 2013).

Biocompatibility and Nanotoxicity:

Chronic effects on cellular function, tissue integrity, and systemic health remain poorly understood. Degradation products, metal ion leaching, and nanoparticle accumulation pose potential health risks (Xiao *et al.*, 2022; Y. Yang *et al.*, 2024).

Environmental Safety and Ecotoxicology:

Concerns regarding persistence, bioaccumulation potential, and ecological impacts require comprehensive life-cycle assessments, environmental fate modeling, and ecotoxicological studies (Tripathy & Pradhan, 2025; Xie *et al.*, 2024).

Regulatory Approval and Standardization:

Lack of standardized testing protocols, universally accepted performance metrics, and established regulatory frameworks impedes commercial development.

Multifunctionality Integration:

Achieving simultaneous optimization of healing efficiency, mechanical robustness, electrical conductivity, catalytic activity, and biocompatibility remains challenging (X. Li *et al.*, 2024; Zhao *et al.*, 2021).

Mechanism Elucidation:

Molecular mechanisms governing autonomous healing remain incompletely understood. Integration of experimental observations with computational modeling will provide mechanistic insights essential for rational material design (C. Chen *et al.*, 2020; Ludwig *et al.*, 2023).

Cost-Effectiveness:

Comprehensive techno-economic analyses and life-cycle cost assessments are needed to establish economic viability and identify cost-reduction opportunities.

Future Research Directions:

Emerging directions include multistimuli-responsive systems, self-healing nanorobotics, digital twins, autonomous materials discovery platforms, sustainable and biodegradable systems, biohybrid self-healing materials, 4D printing, quantum-enhanced self-healing, nature-inspired hierarchical design, and intensified clinical translation efforts (Huang *et al.*, 2024; Ludwig *et al.*, 2023; Song *et al.*, 2024).

12. CONCLUSION

Bio-inspired self-healing nanostructures reframe material durability: instead of resisting damage indefinitely, they recover from it repeatedly, borrowing the same reversible-chemistry logic biology has used for far longer. This has already produced real gains photocatalysts and membranes that sustain pollutant removal across many more cycles than conventional materials, and biosensors, wearables, and implants that tolerate continuous use without losing accuracy.

The next phase of progress lies less in discovering new healing chemistries and more in integration: AI-guided design, multifunctional platforms combining sensing and degradation, and manufacturing that can actually scale. The remaining challenges long-

term stability, nanotoxicity, and regulatory standardization are the ordinary work of turning a materials science advance into a deployable technology, and how well that work is done will decide how much of this field's promise becomes real-world impact.

REFERENCES

- Ahn, B. K., Lee, D. W., Israelachvili, J. N., & Waite, J. H. (2014). Surface-initiated self-healing of polymers in aqueous media. *Nature Materials*, 13(9), 867–872.
- Cai, Y., Shen, J., Yang, C. W., Wan, J., Tan, H. R., Hendrickson, J., et al. (2020). Mixed-dimensional MXene-hydrogel heterostructures for electronic skin sensors with ultrabroad working range. *Science Advances*, 6(48), eabb5367.
- Chae, A., Murali, G., Lee, S. Y., Gwak, J., Kim, S. J., Jeong, Y. J., et al. (2023). Highly oxidation-resistant and self-healable MXene-based hydrogels for wearable strain sensor. *Advanced Functional Materials*, 33(24), 2213382.
- Chen, C., Zuo, Y., Ye, W., Li, X., Deng, Z., & Ong, S. P. (2020). A critical review of machine learning for energy materials. *Advanced Energy Materials*, 10(8), 1903242.
- Chen, X., Dam, M. A., Ono, K., Mal, A., Shen, H., Nutt, S. R., et al. (2002). A thermally re-mendable cross-linked polymeric material. *Science*, 295(5560), 1698–1702.
- Dalei, G., Jena, D., Das, B. R., & Das, S. (2024). Bio-valORIZATION of Tagetes floral waste extract in fabrication of self-healing Schiff-base nanocomposite hydrogels for colon cancer remedy. *Environmental Science and Pollution Research International*, 31(3), 4330–4347.
- Han, L., Gong, L., Chen, J., Zhang, J., Xiang, L., Zhang, L., et al. (2018). Universal mussel-inspired ultrastable surface-anchoring strategy via adaptive synergy of catechol and cations. *ACS Applied Materials & Interfaces*, 10(3), 2166–2173.
- Holten-Andersen, N., Harrington, M. J., Birkedal, H., Lee, B. P., Messersmith, P. B., Lee, K. Y. C., et al. (2011). pH-induced metal-ligand cross-links inspired by mussel yield self-healing polymer networks with near-covalent elastic moduli. *Proceedings of the National Academy of Sciences*, 108(7), 2651–2655.
- Huang, J., Xu, Z., Qiu, Y., Cheng, J., Zhao, W., & Zhang, X. (2024). Self-healing flexible electronics. *Advanced Materials*, 36(8), 2307435.
- Kausar, A. (2021). Self-healing polymer/carbon nanotube nanocomposite: A review. *Journal of Reinforced Plastics and Composites*, 40(19–20), 731–748.
- Li, L., Ji, X., & Chen, K. (2023). Conductive, self-healing, and antibacterial Ag/MXene-PVA hydrogel as wearable skin-like sensors. *Journal of Industrial Textiles*, 53, 15280837231156184.
- Li, S., Mao, W., Xia, L., et al. (2023). An injectable, self-healing and degradable hydrogel scaffold as a functional biocompatible material for tissue engineering applications. *Journal of Materials Science*, 58, 6710–6726.
- Li, X., Wang, Y., & Zhang, X. (2024). Strong, healable materials with bio-like ordered architectures and versatile functionality. *SusMat*, 4, e248.
- Liu, Y., & Hsu, S. H. (2023). Biomimetic self-healing hydrogels for tissue engineering applications. *Biomaterials*, 292, 121943.
- Louis, J., et al. (2021). Graphene coupled TiO2 photocatalysts for environmental applications: A review. *Chemosphere*, 272, 129866.
- Ludwig, N., et al. (2023). Applied machine learning as a driver for polymeric biomaterials design. *Nature Communications*, 14, 4838.
- Nejati, S., & Mongeau, L. (2023). Injectable, pore-forming, self-healing, and adhesive hyaluronan hydrogels for soft tissue engineering applications. *Scientific Reports*, 13, 14303.
- Self, J. L., Reynolds, V. G., Blankenship, J., Mee, E., Guo, J., Albanese, K., et al. (2023). Conductive and self-healing carbon nanotube-polymer composites for mechanically strong smart materials. *ACS Applied Nano Materials*, 6(2), 986–994.
- Song, J., et al. (2024). Thermoelectric self-healing polymer composite inspired by skin thermal sensory system. *Advanced Materials*, 36(15), 2308456.
- Sun, P., Ren, S., Liu, F., Wu, A., Sun, N., Shi, L., et al. (2018). Smart low molecular weight hydrogels with dynamic covalent skeletons. *Soft Matter*, 14(32), 6678–6683.
- Talebian, S., Mehrli, M., Taebnia, N., Pennisi, C. P., Kadumudi, F. B., Foroughi, J., et al. (2019). Self-healing hydrogels: The next paradigm shift in tissue engineering? *Advanced Science*, 6(16), 1900552.
- Tripathy, D. B., & Pradhan, S. (2025). Self-healing membranes: Smart materials for water remediation and desalination. *Water Environment Research*, 97(8), e70148.
- Tu, W., Luo, Y., Shen, J., Ran, X., Yu, Z., Wang, C., et al. (2025). Lotus leaf-inspired corrosion-resistant and robust superhydrophobic coating for oil-water separation. *Biomimetics*, 10(5), 262.
- Waite, J. H., Andersen, N. H., Jewhurst, S., & Sun, C. J. (2005). Mussel adhesion: Finding the tricks worth mimicking. *Journal of Adhesion*, 81(3–4), 297–317.
- Wang, C., Xia, K., Wang, H., Liang, X., Yin, Z., & Zhang, Y. (2019). Advanced carbon for flexible and wearable electronics. *Advanced Materials*, 31(9), 1801072.
- Wang, S., & Urban, M. W. (2020). Self-healing polymers. *Nature Reviews Materials*, 5(8), 562–583.
- White, S. R., Sottos, N. R., Geubelle, P. H., Moore, J. S., Kessler, M. R., Sriram, S. R., et al. (2001).

Autonomic healing of polymer composites. *Nature*, 409(6822), 794–797.

- Wu, M., Han, L., Yan, B., & Zeng, H. (2023). Self-healing hydrogels based on reversible noncovalent and dynamic covalent interactions: A short review. *Supramolecular Materials*, 2, 100045.
- Xiao, Y., *et al.*(2022). Ag/MoS2 nanozyme-modified hydrogel with adhesion and self-healing abilities for bacterial clearance and wound healing. *ACS Applied Materials & Interfaces*, 14(45), 50626–50638.
- Xie, Y., Zhang, T., Wang, B., & Wang, W. (2024). The application of metal–organic frameworks in water treatment and their large-scale preparation: A review. *Materials*, 17(9), 1972.
- Xu, J., & Hsu, S. H. (2023). Self-healing hydrogel as an injectable implant: Translation in brain diseases. *Journal of Biomedical Science*, 30, 47.
- Yang, C., Xue, Z., & Wen, J. (2023). Recent advances in MOF-based materials for remediation of heavy metals and organic pollutants: Insights into performance, mechanisms, and future opportunities. *Sustainability*, 15(8), 6686.
- Yang, Y., & Urban, M. W. (2013). Self-healing polymeric materials. *Chemical Society Reviews*, 42(17), 7446–7467.
- Yang, Y., Wang, J., Huang, S., Li, M., Chen, J., Pei, D., *et al.*(2024). Bacteria-responsive programmed self-activating antibacterial hydrogel to remodel regeneration microenvironment for infected wound healing. *National Science Review*, 11(4), nwae044.
- Yu, J., Kan, Y., Rapp, M., Danner, E., Wei, W., Das, S., *et al.*(2013). Adaptive hydrophobic and hydrophilic interactions of mussel foot proteins with organic thin films. *Proceedings of the National Academy of Sciences*, 110(39), 15680–15685.
- Yuan, Y., Li, S., & Zhu, L. (2024). The use of bimetallic metal–organic frameworks as restoration materials for pollutants removal from water environment. *Royal Society Open Science*, 11(7), 240380.
- Zamal, H. H., Barba, D., Aïssa, B., Haddad, E., & Rosei, F. (2020). Recovery of electro-mechanical properties inside self-healing composites through microencapsulation of carbon nanotubes. *Scientific Reports*, 10, 2942.
- Zhang, G., Zhao, Q., Zou, W., Luo, Y., & Li, Y. (2022). Self-healing hydrogels based on dynamic covalent chemistry. *Advanced Materials*, 34(23), 2201100.
- Zhang, Y. Z., El-Demellawi, J. K., Jiang, Q., Ge, G., Liang, H., Lee, K., *et al.*(2020). MXene hydrogels: Fundamentals and applications. *Chemical Society Reviews*, 49(20), 7229–7251.
- Zhao, X., Liu, Y., & Shao, Z. (2021). Recent advances in bioinspired self-healing materials. *Materials Horizons*, 8(6), 1666–1687.